

Ethylene Propylene Diene Terpolymer

KUMHO POLYCHEM

Product Data Sheet

Product Description	Features
KEP2320 is an EPDM rubber with Broad molecular weight distribution, low ethylene contents. It can be used to LV/MV electrical insulation, brake parts, gasket, corner molding, mandrel, mold sponge.	- Excellent roll processability - Good processing even without oil - Excellent extrusion properties - Good electrical properties - Excellent low temperature flexibility

Test items	Sale Specifications	Unit	Test Method
Volatile Matter	Max 0.75	wt %	ASTM D5668
Mooney Viscosity ML(1+4)@125 °C	25.0 ± 4.0	MU	ASTM D1646
Ethylene Contents	57.5 ± 3.0	wt %	ASTM D3900
ENB Contents	4.7 ± 0.6	wt %	ASTM D6047

Other Products Features

Product Form	Bale
Packaging	25 kg/Bag in Mesh Box, LDPE, EOM film, 750 kg (25 kg × 30)
Shelf Life	24 months from date of production at room temperature in dry condition, exposure to light has to be avoided
The Others	RoHS Free

Contact Information

Head Office	East Wing, Signature Tower, #100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea 82-2-6961-1114
Plant	613 Sandanjungang-ro, Yeosu, Jeonnam, Korea 82-61-688-2821
Revision Date	01/01/2025
Revision No.	13